

Basonat[®] HB 175 MP/X

Product Description	Basonat HB 175 MP/X is an aliphatic polyisocyanate for lightfast and weather-resistant two-pack polyurethane coatings. It is an approximately 75% solids solution in a 1:1 blend of 1-methoxy-2-propyl acetate and xylene.
Key Features & Benefits	<ul style="list-style-type: none">- Excellent weather and chemical resistance- Excellent physical properties- Non-yellowing
Chemical Composition	Polyisocyanate based on biuret-modified hexamethylene diisocyanate (HDI)

Properties

Typical Characteristics

Appearance		liquid
Non-volatile	%	74 – 76
Viscosity at 23°C	cps	130 – 300
Shear rate D	s ⁻¹	1,000
Hazen color number		≤ 30
Density at 20°C	g/cm ³ , lbs/gal	1.07, 8.93
NCO content	%	16 – 17
NCO equivalent weight (as supplied)		~ 255

Crosslinking

Used to crosslink most hydroxy-containing resins such as Joncryl[®] acrylics and hydroxy functional polyesters.

Diluent tolerance

Can be diluted with esters, ketones, glycoether acetates or with aromatic hydrocarbons. Only urethane-grade solvents should be used to lessen the possibility of reacting with water.

If diluted to a polyisocyanate fraction of less than 40%, turbidity, flocculation, and/or sedimentation may occur during storage. Storage trials should always be conducted.

The NCO equivalent weight indicates the amount of Basonat polyisocyanate as supplied containing 1 Mol of active NCO.

These values should not be interpreted as specifications.

Applications

Basonat HB 175 MP/X is used to formulate lightfast and weather-resistant coatings. Aliphatic polyisocyanates are sometimes even used in primers for difficult substrates such as aluminum or plastics.

Basonat HB 175 MP/X is recommended for applications such as:

- Interior/exterior general industrial metal coating applications
- Interior/exterior plastic component coating applications
- Interior/exterior wood coatings for floor, furniture, or millwork applications
- Interior/exterior Automotive OEM or refinish applications

Processing

The theoretical equivalent amount of polyisocyanate required for crosslinking is computed using the formula below:

$$\frac{0.075 \times [\text{OH number}] \times [\% \text{ non-volatile fraction of OH component}]}{[\% \text{ NCO}]}$$

Example

Basonat HB 175 MP/X and Joncryl 922

Joncryl 922

OH number	140 mg KOH/g polyol on solids
Non-volatile fraction, Nv	80%
NCO content (Basonat HB 175 MP/X)	16.5%

$$\frac{0.075 \times 140 \times 80}{16.5} = 50.9$$

Basonat HB 175 MP/X dosage rate for 100g Joncryl 922 as supplied = 50.9g.

Solvents, pigments, or extenders, etc. used should be free from compounds containing active hydrogen groups such as water, alcohols, or amines.

A water content of less than 500 ppm in solvents and binders in two-component polyurethane coatings is acceptable.

Safety**General**

The usual safety precautions when handling chemicals must be observed. These include the measures described in Federal, State, and Local health and safety regulations, thorough ventilation of the workplace, good skin care practices, and wearing of protective goggles.

Safety Data Sheet

All safety information is provided in the Safety Data Sheet for Basonat HB 175 MP/X.

Storage

Please refer to the "Handling and Storage of Polymer Dispersion" brochure

Important

While the descriptions, designs, data and information contained herein are presented in good faith and believed to be accurate, they are provided for guidance only. Because many factors may affect processing or application/use, BASF recommends that the reader make tests to determine the suitability of a product for a particular purpose prior to use. **NO WARRANTIES OF ANY KIND, EITHER EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH, OR THAT THE PRODUCTS, DESCRIPTIONS, DESIGNS, DATA OR INFORMATION MAY BE USED WITHOUT INFRINGING THE INTELLECTUAL PROPERTY RIGHTS OF OTHERS.** In no case shall the descriptions, information, data or designs provided be considered a part of BASF's terms and conditions of sale. Further, the descriptions, designs, data, and information furnished by BASF hereunder are given gratis and BASF assumes no obligation or liability for the descriptions, designs, data or information given or results obtained, all such being given and accepted at the reader's risk.

Basonat and Joncryl are registered trademarks of BASF Group.

© BASF Corporation, 2019



BASF Corporation is fully committed to the Responsible Care® initiative in the USA, Canada, and Mexico.
For more information on Responsible Care, go to:
U.S.: www.basf.us/responsiblecare_usa
Canada: www.basf.us/responsiblecare_canada
México: www.basf.us/responsiblecare_mexico

U.S & Canada

BASF Corporation
24710 W Eleven Mile Road
Southfield, MI 48034
ph: 1(800) 231-7868
fax:1(800) 392-7429
Email: CustCare-Charlotte@basf.com
Email: edtech-info@basf.com
www.basf.us/dpsolutions

Mexico

BASF Mexicana, S.A. de C.V.
Av. Insurgentes Sur # 975
Col. Ciudad de los Deportes
C.P. 03710
Mexico, D.F.
Phone: (52-55) 5325-2756
Fax: (52-55) 5723-3011