

Butofan[®] NS 299

Chemical Nature **Aqueous non-carboxylated butadiene-styrene copolymer dispersion for use in flooring adhesives and asphalt modification**

Properties

Typical Properties

Solids Content	%	~ 54.0
pH		~ 11.4
Viscosity (Brookfield LV, Spindle #2, at 30 rpm)	mPa s	~ 100 – 600
Glass Transition Temperature (DSC)	°C	- 16

Other properties of the dispersion

Density	lbs/gal	ca. 8.3
Bound Styrene	%	ca. 50
Residual Styrene	%	0.05 max
Surface tension	mN/m	ca. 49
Average particle size	microns	ca. 0.15
Dispersion type		anionic
Antioxidant		none
Mechanical strength*		
Tensile strength	psi	ca. 75
Elongation at break	%	ca. 900
Surface		tacky
Dispersion type		anionic
Stabilizer type		rosin acid

*This figure should be taken for comparison purposes only. All that can be obtained from it is an idea of the magnitude concerned.

Compatible with

<i>Polymer Dispersions</i>	Butofan [®] NS 209, Butofan [®] NS 222, Butonal [®] NS 104, Styrofan [®] ND 593
<i>Thickeners</i>	Rheovis [®] AS 1125
<i>Other Resins</i>	Commercial hydrocarbon tackifier dispersions.

Safety

General

The usual safety precautions when handling chemicals must be observed. These include the measures described in Federal, State and Local health and safety regulations, thorough ventilation of the workplace, good skin care and wearing of protective goggles.

Safety Data Sheet

All safety information is provided in the Safety Data Sheet for Butofan NS 299.

Storage

Please refer to the "Handling and Storage of Polymer Dispersions" brochure.

Important

The descriptions, designs, and data contained herein are presented for your guidance only. Because there are many factors under your control which may affect processing or application/use it is necessary for you to make appropriate tests to determine whether the product is suitable for your particular purpose prior to use. **NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, OR INFORMATION SET FORTH, OR THAT THE PRODUCTS, DESIGNS, OR DATA MAY BE USED WITHOUT INFRINGING THE INTELLECTUAL PROPERTY RIGHTS OF OTHERS. IN NO CASE SHALL THE DESCRIPTIONS, DATA OR DESIGNS PROVIDED BE PRESUMED TO BE A PART OF OUR TERMS AND CONDITIONS OF SALE.** Further, you expressly understand and agree that the descriptions, designs, and data furnished by BASF hereunder are given gratis and BASF assumes no obligation or liability for same or results obtained from use thereof, all such being given to you and accepted by you at your risk.

Butofan is a registered trademark of BASF Group.

© BASF Corporation, 2018



BASF Corporation is fully committed to the Responsible Care® initiative in the USA, Canada, and Mexico.

For more information on Responsible Care® go to:

U.S.: www.basf.us/responsiblecare_usa

Canada: www.basf.us/responsiblecare_canada

México: www.basf.us/responsiblecare_mexico

U.S & Canada

BASF Corporation
24710 W Eleven Mile Road
Southfield, MI 48034
ph: 1(800) 231-7868
fax:1(800) 392-7429
Email: CustCare-Charlotte@basf.com
Email: edtech-info@basf.com
www.basf.us/dpsolutions

Mexico

BASF Mexicana, S.A. de C.V.
Av. Insurgentes Sur # 975
Col. Ciudad de los Deportes
C.P. 03710
Mexico, D.F.
Phone: (52-55) 5325-2756
Fax: (52-55) 5723-3011