

Butonal[®] NS 104

Chemical Nature Cold polymerized, non-carboxylated, fatty acid stabilized styrene-butadiene copolymer dispersion for the manufacture of flooring adhesives and latex foam

Properties

Typical Properties	Solids Content	%	~ 71.0
	pH		~ 10.4
	Viscosity at 23 °C (Brookfield LV, Spindle #3, at 30 rpm)	mPa s	~ 1000 – 1500
Other properties of the dispersion	Density	lbs/gal	ca. 8.00
	Bound Styrene	%	ca. 24
	Residual Styrene	%	0.08 max.
	Surface Tension	mN/m	ca. 34
	Type of Dispersion		anionic
Antioxidant		none	
Properties of the Film	Mechanical Strength*		
	Tensile Strength	psi	ca. 65
	Elongation at Break	%	ca. 400
	Surface		non-tacky

* These figures should be taken for comparison purposes only. All that can be obtained from it is an idea of the order of magnitude concerned.

Compatible With

<i>Dispersions</i>	Butofan [®] NS 209, NS 222, Styrofan [®] ND 593, Styronal [®] ND 811
<i>Thickeners</i>	Rheovis [®] AS 1125
<i>Resins</i>	Commercial hydrocarbon tackifier dispersions

Application

Fields of Application	Butonal NS 104 is used in the manufacture of flooring adhesives. Butonal NS 104 is a high-molecular weight polymer dispersion which gives excellent legging characteristics in flooring adhesives.
Processing	In general, additives should be pre-neutralized to pH > 8.5 - 9.0 (depending on the system) prior to blending with Butonal NS 104. The exact conditions should be determined by laboratory trials.

Safety

General

The usual safety precautions when handling chemicals must be observed. These include the measures described in Federal, State and Local health and safety regulations, thorough ventilation of the workplace, good skin care and wearing of protective goggles.

Safety Data Sheet

All safety information is provided in the Safety Data Sheet for Butonal NS 104

Storage

Please refer to the "Handling and Storage of Polymer Dispersions" brochure.

Important

The descriptions, designs, and data contained herein are presented for your guidance only. Because there are many factors under your control which may affect processing or application/use it is necessary for you to make appropriate tests to determine whether the product is suitable for your particular purpose prior to use. **NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, OR INFORMATION SET FORTH, OR THAT THE PRODUCTS, DESIGNS, OR DATA MAY BE USED WITHOUT INFRINGING THE INTELLECTUAL PROPERTY RIGHTS OF OTHERS. IN NO CASE SHALL THE DESCRIPTIONS, DATA OR DESIGNS PROVIDED BE PRESUMED TO BE A PART OF OUR TERMS AND CONDITIONS OF SALE.** Further, you expressly understand and agree that the descriptions, designs, and data furnished by BASF hereunder are given gratis and BASF assumes no obligation or liability for same or results obtained from use thereof, all such being given to you and accepted by you at your risk.

Butonal is a registered trademark of BASF Group.

© BASF Corporation, 2018



BASF Corporation is fully committed to the Responsible Care® initiative in the USA, Canada, and Mexico. For more information on Responsible Care® go to:
U.S.: www.basf.us/responsiblecare_usa
Canada: www.basf.us/responsiblecare_canada
México: www.basf.us/responsiblecare_mexico

BASF Corporation
Dispersions and Resins
11501 Steele Creek Road
Charlotte, North Carolina 28273
Phone: (800) 251 – 0612
Email: CustCare-Charlotte@basf.com
Email: edtech-info@basf.com
www.basf.us/formulation-additives