

Butonal[®] NS 175

Chemical Nature **Aqueous, high solids, cold-polymerized, anionic styrene-butadiene dispersion for modifying asphalt cements and anionic asphalt emulsions**

Properties

Typical Properties	Solids content	%	~ 71.0
	pH		~ 10.5
	Viscosity (Brookfield RVT, Spindle #3, at 20 rpm)	mPa s	1000 – 1500
Other properties of the dispersion	Bound styrene	%	24
	Residual monomer	%	0.08 max.
	Surface tension	mN/m	34
	Antioxidant		none
	Glass transition temperature (DSC)	°C	-53
	Weight/volume	lb/gal	~ 8.07
	Specific Gravity		~ 0.97

* The above values should not be taken as specification

Application

Features

Butonal NS 175 is a mechanically stable latex polymer dispersion that can be readily pre-blended into hot asphalt cement in order to meet Superpave[®] "Plus" modified binder specifications as well as to provide improvements in conventional properties such as increased softening point and decreased penetration. It can also be used to modify asphalt cement at the hot mix plant via addition directly to the pug mill (batch HMA plant) following asphalt addition or injection into the asphalt line prior to entering the drum (continuous HMA plant). Butonal[®] NS 175 is also particularly effective at increasing asphalt viscosity and is utilized to produce modified binders for use in OGFC mixes to prevent drain-down.

Butonal NS 175 can also be incorporated into anionic asphalt emulsions via addition to the soap solution (batch process) or co-milling (continuous process).

Processing

Butonal NS 175 can be used in the following applications:

- PG-graded binders
- OGFC binders
- Chip seal
- Slurry seal
- Below-grade foundation waterproofing

Periodic mechanical stirring is required to maintain a homogeneous mixture. Some separation is possible due to the specific gravity and particle size distribution of these dispersions.

Generally, the preferred means of stirring is with a separate propeller type stirrer. This low-speed, low-shear mechanical stirrer can be located off-center, set at an angle, or side mounted near the bottom to prevent foaming or vortexing. Center stirring requires tank baffles. It is recommended that

the material be agitated for 10 - 20 minutes every 24 hours when the material is being used in production.

Safety

General

The usual safety precautions when handling chemicals must be observed. These include the measures described in Federal, State and Local health and safety regulations, thorough ventilation of the workplace, good skin care and wearing of protective goggles.

Safety Data Sheet

All safety information is provided in the Safety Data Sheet for Butonal NS 175.

Storage

Please refer to the "Handling and Storage of Polymer Dispersions" brochure.

Important

The descriptions, designs, and data contained herein are presented for your guidance only. Because there are many factors under your control which may affect processing or application/use it is necessary for you to make appropriate tests to determine whether the product is suitable for your particular purpose prior to use. **NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, OR INFORMATION SET FORTH, OR THAT THE PRODUCTS, DESIGNS, OR DATA MAY BE USED WITHOUT INFRINGING THE INTELLECTUAL PROPERTY RIGHTS OF OTHERS. IN NO CASE SHALL THE DESCRIPTIONS, DATA OR DESIGNS PROVIDED BE PRESUMED TO BE A PART OF OUR TERMS AND CONDITIONS OF SALE.** Further, you expressly understand and agree that the descriptions, designs, and data furnished by BASF hereunder are given gratis and BASF assumes no obligation or liability for same or results obtained from use thereof, all such being given to you and accepted by you at your risk.

Butonal is a registered trademark of BASF Group.

© BASF Corporation, 2020



BASF Corporation is fully committed to the Responsible Care® initiative in the USA, Canada, and Mexico. For more information on Responsible Care® go to:
U.S.: www.basf.us/responsiblecare_usa
Canada: www.basf.us/responsiblecare_canada
México: www.basf.us/responsiblecare_mexico

BASF Corporation
Dispersions and Resins
11501 Steele Creek Road
Charlotte, North Carolina 28273
Phone: (800) 251 – 0612
Email: CustCare-Charlotte@basf.com
Email: edtech-info@basf.com
www.basf.us/formulation-additives