

# Dispex<sup>®</sup> Ultra CX 4452

**Product description** Dispex<sup>®</sup> Ultra CX 4452 is an aqueous, high performance dispersant for inorganic pigments and fillers, such as (transparent) iron oxides and titanium dioxide

**Key benefits**

- Especially designed for inorganic pigments and fillers
- Excellent performance with transparent iron oxide pigments
- Outstanding viscosity reduction and stability
- High pigment loading
- Suitable for low-VOC applications

**Chemical nature** Anionic, high-molecular weight polymer

## Properties

**Physical form** Clear, yellowish liquid

**Technical data**

(not supply specification)

Solvent	Water
Active content	~ 40%

## Application

Dispex® Ultra CX 4452 is a water-borne dispersant for inorganic pigments and fillers, such as (transparent) iron oxides and titanium dioxide. It stabilizes inorganic pigments by means of electro-steric stabilization. It is particularly suitable for the preparation of aqueous resin-free pigment concentrates.

Dispex® Ultra CX 4452 provides strong viscosity reduction during grinding, especially in resin-free pigment concentrates. Due to its broad compatibility characteristics excellent transparency can be achieved.

It is especially recommended for aqueous wood coatings, wood preservation and high-end architectural coatings. Dispex® Ultra CX 4452 can also be used in all kinds of water-borne coatings like general industrial and automotive coatings.

Formulation guideline		
Titanium dioxide	0,5-2,5 %	Dispersant (solid) on pigment
Iron oxide	5-10 %	Dispersant (solid) on pigment
Iron oxide (transparent)	15-25 %	Dispersant (solid) on pigment

## Storage

Separation or turbidity may occur during storage or transportation below 0 °C. Heat to 35–40 °C (95–104 °F) and stir well to re-liquefy.

### Contacts worldwide

Asia  
 BASF East Asia Regional Headquarters Ltd  
 45/F, Jardine House  
 No. 1 Connaught Place  
 Central Hong Kong  
 China  
[formulation-additives-asia@basf.com](mailto:formulation-additives-asia@basf.com)

North America  
 BASF Corporation  
 11501 Steele Creek Road  
 Charlotte, NC 28273  
 USA  
[formulation-additives-nafta@basf.com](mailto:formulation-additives-nafta@basf.com)

Europe  
 BASF SE  
 Formulation Additives  
 67056 Ludwigshafen  
 Germany  
[formulation-additives-europe@basf.com](mailto:formulation-additives-europe@basf.com)

South America  
 BASF S.A.  
 Rochaverá - Crystal Tower  
 Av. das Nações Unidas, 14.171  
 Morumbi - São Paulo-SP  
 Brazil  
[formulation-additives-south-america@basf.com](mailto:formulation-additives-south-america@basf.com)

### Validity

This Technical Data Sheet is valid for all versions of the Dispex® Ultra CX 4452.

### Safety

When handling this product, please comply with the advice and information given in the safety data sheet and observe protective and workplace hygiene measures adequate for handling chemicals.

### Note

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights, etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. The agreed contractual quality of the product results exclusively from the statements made in the product specification. It is the responsibility of the recipient of our product to ensure that any proprietary rights and existing laws and legislation are observed.

® = Registered trademark

™ = Trademark of the BASF Group, unless otherwise noted

[www.basf.com/formulation-additives](http://www.basf.com/formulation-additives)