

Dispex[®] Ultra PA 4503

general

- Dispex[®] Ultra PA 4503 is a dispersing resin with self-emulsifying properties.
- suitable for the production of VOC-free pigment concentrates
- suitable for systems with a wide pH range (5–12)

chemical nature

fatty-acid-modified polymer, free of solvents and volatile amines

Properties

physical form

clear, yellowish liquid

storage

The product should be protected from frost and stored in a cool dry place (0 – 45 °C [32 – 113 °F]).

typical properties (no supply specification)

solvent	water
density at 20 °C (68 °F)	~ 1.08 g/cm ³
active ingredients	~ 75%
color	≤ 6

Application

Dispex[®] Ultra PA 4503 is recommended as a grinding vehicle or in combination with the polymeric dispersants Efka[®] 4550 and Efka[®] 4560, suitable for the production of ultra-low-VOC water-based pigment concentrates.

recommended concentrations

3 parts Dispex[®] Ultra PA 4503 on 1 part dispersing agent (solids on solids)

Contacts worldwide

Asia

BASF East Asia Regional Headquarters Ltd
45/F, Jardine House
No. 1 Connaught Place
Central Hong Kong
China
formulation-additives-asia@basf.com

Europe

BASF SE
Formulation Additives
67056 Ludwigshafen
Germany
formulation-additives-europe@basf.com

North America

BASF Corporation
11501 Steele Creek Road
Charlotte, NC 28273
USA
formulation-additives-nafta@basf.com

South America

BASF S.A
Rochaverá - Crystal Tower
Av. das Nações Unidas, 14.171
Morumbi - São Paulo-SP
Brazil
formulation-additives-south-america@basf.com

Validity

This Technical Data Sheet is valid for all versions of the Dispex Ultra PA 4503.

Safety

When handling these products, please comply with the advice and information given in the safety data sheet and observe protective and workplace hygiene measures adequate for handling chemicals.

Note

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights, etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. The agreed contractual quality of the product results exclusively from the statements made in the product specification. It is the responsibility of the recipient of our product to ensure that any proprietary rights and existing laws and legislation are observed.

® = registered trademark, ™ = trademark of BASF Group, unless otherwise noted