

Efka[®] FL 3770

general

slip and leveling agent

Efka[®] FL 3770, broadly compatible with most solvent-based resins, is a leveling and a very effective anti-cratering agent as well as a flow control agent without foam stabilization.

chemical nature

fluorocarbon-modified polyacrylate

Properties

physical form

clear, colorless liquid

storage

Keep container tightly closed and in a cool place.

typical properties (no supply specification)

solids	~ 51%
solvent	alkyl benzene
density at 20 °C (68 °F)	~ 0.96 g/cm ³

Application

With its broad compatibility, Efka[®] FL 3770 can be used in most solvent-based liquid coatings to improve the leveling of the dry film with no negative impact on recoatability. It is designed to be used in:

- two-pack PUR automotive refinish coatings
- polyester/melamine coil coatings
- two-pack epoxy and PUR compounds
- UV-curable wood coatings

recommended concentrations

0.5–2.0% on total formulation

Efka[®] FL 3770 can be incorporated at any stage during the production process

Asia

BASF East Asia Regional Headquarters Ltd

45/F, Jardine House

No. 1 Connaught Place

Central Hong Kong

China

formulation-additives-asia@basf.com

Europe

BASF SE

Formulation Additives

67056 Ludwigshafen

Germany

formulation-additives-europe@basf.com

North America

BASF Corporation

11501 Steele Creek Road

Charlotte, NC 28273

USA

formulation-additives-nafta@basf.com

South America

BASF S.A

Rochaverá - Crystal Tower

Av. das Nações Unidas, 14.171

Morumbi - São Paulo-SP

Brazil

formulation-additives-south-america@basf.com**Validity**

This Technical Data Sheet is valid for all versions of Efka® FL 3770.

Safety

When handling this product, please comply with the advice and information given in the safety data sheet and observe protective and workplace hygiene measures adequate for handling chemicals.

Note

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights, etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. The agreed contractual quality of the product results exclusively from the statements made in the product specification. It is the responsibility of the recipient of our product to ensure that any proprietary rights and existing laws and legislation are observed.

® = registered trademark, ™ = trademark of the BASF Group, unless otherwise noted