

Efka® PU 4010



general

high-molecular-weight dispersing agent

Efka® PU 4010 is a polymeric dispersant for stabilizing inorganic pigments including carbon blacks. It also has an excellent performance in many organic pigments. This results in:

- reduced grinding time
- improved gloss
- prevention of flooding and floating
- higher color strength

Due to its particularly good combination of price and performance, Efka® PU 4010 is a very attractive substitute for conventional wetting and dispersing agents.

It is possible to mix combinations of inorganic pigments stabilized with Efka® PU 4010 and organic pigments stabilized with other Efka® high-molecular-weight polymeric dispersants.

chemical nature

modified polyurethane

Properties

physical form

clear, slightly yellowish liquid

storage

Efka® PU 4010 may partially solidify when stored below 10 °C (50 °F). Heat to 35–40 °C (95–104 °F) to reliquify.

typical properties (no supply specification)

solvent	butyl acetate / methoxypropyl acetate / solvent naphta
density at 20 °C	~ 0.98 g/cm ³
active ingredients	~ 50 %
flash point	24 °C
acid value	~ 13 mg KOH/g
amine value	~ 6 mg KOH/g
color	≤ 6

Application

Efka® PU 4010 was developed as a general dispersing agent for all solvent-based paints from high-performance industrial coatings to normal decorative paints. It can also be used in universal solvent-based pigment concentrates.

recommended concentrations

titanium dioxide	2– 4 % as supplied
inorganic pigments	5–10 % as supplied
organic pigments	20–40 % as supplied
carbon blacks	30–60 % as supplied

Efka® PU 4010 should be incorporated in the mill base before adding the pigments.

Contacts worldwide

Asia

BASF East Asia Regional Headquarters Ltd
45/F, Jardine House
No. 1 Connaught Place
Central Hong Kong
China
formulation-additives-asia@basf.com

North America

BASF Corporation
11501 Steele Creek Road
Charlotte, NC 28273
USA
formulation-additives-nafta@basf.com

Europe

BASF SE
Formulation Additives
67056 Ludwigshafen
Germany
formulation-additives-europe@basf.com

South America

BASF S.A
Rochaverá - Crystal Tower
Av. das Nações Unidas, 14.171
Morumbi - São Paulo-SP
Brazil
formulation-additives-south-america@basf.com

Validity

This Technical Data Sheet is valid for all versions of the Efka® PU 4010.
Efka PU 4010, Efka PU 4010 AN.

Safety

When handling these products, please comply with the advice and information given in the safety data sheet and observe protective and workplace hygiene measures adequate for handling chemicals.

Note

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights, etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. The agreed contractual quality of the product results exclusively from the statements made in the product specification. It is the responsibility of the recipient of our product to ensure that any proprietary rights and existing laws and legislation are observed.

® = registered trademark, ™ = trademark of BASF Group, unless otherwise noted