

# Efka<sup>®</sup> PU 4080

**Product description** high-molecular-weight dispersing agent

Efka<sup>®</sup> PU 4080 is a polymeric dispersant for stabilizing inorganic and organic pigments.

**Key benefits**

- improved gloss and DOI
- reduced flooding
- higher color strength
- lower viscosity

**Chemical nature** modified polyurethane

## Properties

**Physical form** clear yellowish liquid

**Technical data**

(no supply specification)

Solvent	butyl acetate / butylglycol acetate / methoxypropyl acetate
Density at 20 °C	~ 0.97 g/cm <sup>3</sup>
Active ingredients	~ 30 %
Flash point	24 °C
Amine value	~ 4 mg KOH/g
Color	~ 10

---

## Application

Efka® PU 4080 is used in all types of solvent-based coatings, particularly high-quality industrial coatings such as automotive topcoats (OEM and refinish), coil coatings and 2-pack polyurethane coating systems. It is also suitable for use in pigment concentrates.

## Formulation guideline

Experience has shown that, compared with other Efka® polymeric dispersants, smaller quantities of Efka® PU 4080 are needed to give optimum results.

Efka® PU 4080 should be incorporated in the mill base before adding the pigments.

---

## Storage

Efka® PU 4080 may partially solidify when stored below 10 °C. Heat to 35 – 40 °C to reliquify.

### Contacts worldwide

Asia  
BASF East Asia Regional Headquarters Ltd  
45/F, Jardine House  
No. 1 Connaught Place  
Central Hong Kong  
China  
[formulation-additives-asia@basf.com](mailto:formulation-additives-asia@basf.com)

North America  
BASF Corporation  
11501 Steele Creek Road  
Charlotte, NC 28273  
USA  
[formulation-additives-nafta@basf.com](mailto:formulation-additives-nafta@basf.com)

Europe  
BASF SE  
Formulation Additives  
67056 Ludwigshafen  
Germany  
[formulation-additives-europe@basf.com](mailto:formulation-additives-europe@basf.com)

South America  
BASF S.A  
Rochaverá - Crystal Tower  
Av. das Nações Unidas, 14.171  
Morumbi - São Paulo-SP  
Brazil  
[formulation-additives-south-america@basf.com](mailto:formulation-additives-south-america@basf.com)

### Validity

This Technical Data Sheet is valid for all versions of the Efka® PU 4080.

### Safety

When handling this product, please comply with the advice and information given in the safety data sheet and observe protective and workplace hygiene measures adequate for handling chemicals.

### Note

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights, etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. The agreed contractual quality of the product results exclusively from the statements made in the product specification. It is the responsibility of the recipient of our product to ensure that any proprietary rights and existing laws and legislation are observed.

® = Registered trademark

™ = Trademark of the BASF Group, unless otherwise noted

[www.basf.com/formulation-additives](http://www.basf.com/formulation-additives)