

Efka[®] SI 2038

Product description Silicone-based defoamer for solvent-based coatings

Chemical nature Solution of defoaming substances containing silicone

Properties

Physical form Clear, colorless liquid

Technical data (no supply specification)	Solvent	Alkyl benzene / methoxypropylacetate / xylene
	Density	at 20 °C (68 °F) ~ 0.885 g/cm ³
	Refractive index	~ 1.490
	Flash point	25 °C (77 °F)

Application

Efka® SI 2038 prevents the formation of foam and blisters during the manufacturing and application of solvent-based wood finishes. It has very good compatibility properties which make it extremely suitable for use in clear coatings. Recommended applications:

- Polyurethane coatings
- Unsaturated polyester systems
- Acid-curable coatings
- NC lacquers

Recommended concentration

0.1 – 0.5 % on total formulation

Efka® SI 2038 can be added prior to processing. If added to the finished product, care should be taken to ensure uniform dispersion.

Storage

The product should be stored in a cool dry place.

Contacts worldwide

Asia
BASF East Asia Regional Headquarters Ltd
45/F, Jardine House
No. 1 Connaught Place
Central Hong Kong
China
formulation-additives-asia@basf.com

North America
BASF Corporation
11501 Steele Creek Road
Charlotte, NC 28273
USA
formulation-additives-nafta@basf.com

Europe
BASF SE
Formulation Additives
67056 Ludwigshafen
Germany
formulation-additives-europe@basf.com

South America
BASF S.A
Rochaverá - Crystal Tower
Av. das Nações Unidas, 14.171
Morumbi - São Paulo-SP
Brazil
formulation-additives-south-america@basf.com

Validity

This Technical Data Sheet is valid for all versions of the Efka® SI 2038.

Safety

When handling this product, please comply with the advice and information given in the safety data sheet and observe protective and workplace hygiene measures adequate for handling chemicals.

Note

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights, etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. The agreed contractual quality of the product results exclusively from the statements made in the product specification. It is the responsibility of the recipient of our product to ensure that any proprietary rights and existing laws and legislation are observed.

® = Registered trademark

™ = Trademark of the BASF Group, unless otherwise noted

www.basf.com/formulation-additives