

Efka® SI 2723

general

defoamer

- developed to produce rapid de-aeration of solvent-free polyurethane and epoxy compounds
- excellent results in flooring applications so that foam- and blister-free self-leveling coatings can be produced
- acts as a leveling agent, giving a smooth surface to the coating
- low odor

chemical nature

solution of defoaming substances containing silicone

Properties

physical form

colorless, slightly hazy liquid

storage

Efka® SI 2723 should be stored in a cool dry place.

typical properties (no supply specification)

flash point	77 °C (171 °F)
density at 20 °C (68 °F)	~ 0.83 g/cm ³
refractive index	~ 1.453

Application

Efka® SI 2723 can be used in pigmented or non-pigmented resin systems such as:

- solvent-free epoxy and polyurethane systems, low odor
- high-solids two-pack systems
- solvent-free radiation-curable systems

recommended concentrations

0.5–1.5% on total formulation

Efka® SI 2723 can be incorporated prior to processing. If added subsequently, good distribution should be insured.

Contacts worldwide

Asia

BASF East Asia Regional Headquarters Ltd 45/
F, Jardine House
No. 1 Connaught Place
Central Hong Kong
China
formulation-additives-asia@basf.com

North America

BASF Corporation
11501 Steele Creek Road
Charlotte, NC 28273
USA
formulation-additives-nafta@basf.com

Europe

BASF SE
Formulation Additives
67056 Ludwigshafen
Germany
formulation-additives-europe@basf.com

South America

BASF S.A
Rochaverá - Crystal Tower
Av. das Nações Unidas, 14.171
Morumbi - São Paulo-SP
Brazil
formulation-additives-south-america@basf.com

Validity

This Technical Data Sheet is valid for all versions of the Efka® SI 2723.

Safety

When handling these products, please comply with the advice and information given in the safety data sheet and observe protective and workplace hygiene measures adequate for handling chemicals.

Note

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights, etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. The agreed contractual quality of the product results exclusively from the statements made in the product specification. It is the responsibility of the recipient of our product to ensure that any proprietary rights and existing laws and legislation are observed.

® = registered trademark, ™ = trademark of BASF Group, unless otherwise noted

www.basf.com/formulation-additives