### **Technical Information**

# Efka® SL 3030



general slip and leveling agent

Efka® SL 3030 is universally compatible with various coating systems and does not cause cratering even in high concentrations. It has the following benefits:

- improved leveling
- increased scratch and abrasion resistance
- · prevention of floating
- · improved antiblocking characteristics
- · acts as a defoamer and de-aeration aid

**chemical nature** organically modified polysiloxane

## **Properties**

physical form clear, colorless liquid

**storage** Efka® SL 3030 should be stored in a cool dry place.

typical properties (no supply specification)

active ingredients	~ 51%
solvent	isobutanol
density at 20 °C (68 °F)	~ 0.91 g/cm <sup>3</sup>
refractive index	~ 1.494
flash point	27 °C (81°F)

## **Application**

Efka® SL 3030 can be used in water- and solvent-based industrial

coatings, particularly for spray applications.

recommended concentrations 0.1–0.3% of

0.1-0.3% on total formulation

Efka® SL 3030 can be added at any stage during the production process. When added during the dispersion process, it speeds up wetting.

December 2016 page 2 of 2 Efka® SL 3030

#### Contacts worldwide

Asia

BASF East Asia Regional Headquarters Ltd

45/F, Jardine House No. 1 Connaught Place Central Hong Kong

China

formulation-additives-asia@basf.com

Europe BASF SE

Formulation Additives 67056 Ludwigshafen

Germany

formulation-additives-europe@basf.com

North America BASF Corporation 11501 Steele Creek Road Charlotte, NC 28273

USA

formulation-additives-nafta@basf.com

South America BASF S.A

Rochaverá - Crystal Tower Av. das Naçoes Unidas, 14.171 Morumbi - São Paulo-SP

Brazil

formulation-additives-south-america@basf.com

## Validity

This Technical Data Sheet is valid for all versions of the Efka® SL 3030.

#### Safety

When handling these products, please comply with the advice and information given in the safety data sheet and observe protective and workplace hygiene measures adequate for handling chemicals.

#### Note

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights, etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. The agreed contractual quality of the product results exclusively from the statements made in the product specification. It is the responsibility of the recipient of our product to ensure that any proprietary rights and existing laws and legislation are observed.

 $<sup>^{\</sup>circledR}$  = registered trademark,  $^{\intercal M}$  = trademark of BASF Group, unless otherwise noted