Efka[®] SL 3033



general	slip and leveling agent	
	Efka [®] SL 3033 is a very effective additive, which increases slip and surface smoothness. It has excellent compatibility properties, making it very suitable for use in clear coatings, and it	
	improves leveling	
	 increases scratch and abrasion resistance prevents floating enhances anti-blocking characteristics 	
	 prevents cratering 	
chemical nature	organically modified polysiloxane	
Properties		
physical form	clear liquid	
storage	Efka [®] SL 3033 should be stored in a cool dry place.	
typical properties	active ingredients	~ 15%
(no supply specification)	density at 20 °C (68 °F)	~ 0.91 g/cm ³
	refractive index	~ 1.405
	flash point	24 °C (61°F)
	color	≤ 1
Application		

0.1–1.0% on total formulation

Efka® SL 3033 is recommended for all kinds of solvent-based coatings.

recommended concentrations

Efka $^{\ensuremath{\circledast}}$ SL 3033 can be added at any stage during the production process. It speeds up wetting when added during the dispersion process.

Contacts worldwide

Asia

BASF East Asia Regional Headquarters Ltd 45/F, Jardine House No. 1 Connaught Place Central Hong Kong China formulation-additives-asia@basf.com

Europe BASF SE Formulation Additives 67056 Ludwigshafen Germany formulation-additives-europe@basf.com North America BASF Corporation 11501 Steele Creek Road Charlotte, NC 28273 USA formulation-additives-nafta@basf.com

South America BASF S.A Rochaverá - Crystal Tower Av. das Naçoes Unidas, 14.171 Morumbi - São Paulo-SP Brazil formulation-additives-south-america@basf.com

Validity

This Technical Data Sheet is valid for all versions of the Efka® SL 3033.

Safety

When handling these products, please comply with the advice and information given in the safety data sheet and observe protective and workplace hygiene measures adequate for handling chemicals.

Note

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights, etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. The agreed contractual quality of the product results exclusively from the statements made in the product specification. It is the responsibility of the recipient of our product to ensure that any proprietary rights and existing laws and legislation are observed.

[®] = registered trademark, [™] = trademark of BASF Group, unless otherwise noted