

# Hydropalat<sup>®</sup> WE 3104

**Product description**      low foaming wetting agent

- Key benefits**
- Excellent substrate wetting characteristics
  - Low foaming
  - Highly dynamic, nonionic surfactant

**Chemical nature**            2,4,7,9-Tetramethyldec-5-yne-4,7-diol (TMDD)

## Properties

**Physical form**                solid

<b>Technical data</b> (no supply specification)	assay	GC	>98 %
	melting range		40 – 50 °C
	density	at 20°C	~ 0.89 g/cm <sup>3</sup>
	solubility in water	at 25°C	~ 0.17 w%
	surface tension	0.1% in water	~ 33 mN/m

---

## Application

Low foaming wetting agent for all kinds of aqueous coatings, inks, cements.

Hydropalat® WE 3104 can also be used as pigment grinding additive.

**Formulation guideline**    0.05 – 3.0 % on total formulation

---

## Storage

Keep container tightly closed in a cool, well-ventilated place. Keep container dry.

### Contacts worldwide

Asia  
BASF East Asia Regional Headquarters Ltd  
45/F, Jardine House  
No. 1 Connaught Place  
Central Hong Kong  
China  
[formulation-additives-asia@basf.com](mailto:formulation-additives-asia@basf.com)

North America  
BASF Corporation  
11501 Steele Creek Road  
Charlotte, NC 28273  
USA  
[formulation-additives-nafta@basf.com](mailto:formulation-additives-nafta@basf.com)

Europe  
BASF SE  
Formulation Additives  
67056 Ludwigshafen  
Germany  
[formulation-additives-europe@basf.com](mailto:formulation-additives-europe@basf.com)

South America  
BASF S.A  
Rochaverá - Crystal Tower  
Av. das Nações Unidas, 14.171  
Morumbi - São Paulo-SP  
Brazil  
[formulation-additives-south-america@basf.com](mailto:formulation-additives-south-america@basf.com)

### Validity

This Technical Data Sheet is valid for all versions of the Hydropalat® WE 3104.

### Safety

When handling this product, please comply with the advice and information given in the safety data sheet and observe protective and workplace hygiene measures adequate for handling chemicals.

### Note

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights, etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. The agreed contractual quality of the product results exclusively from the statements made in the product specification. It is the responsibility of the recipient of our product to ensure that any proprietary rights and existing laws and legislation are observed.

® = Registered trademark

™ = Trademark of the BASF Group, unless otherwise noted

[www.basf.com/formulation-additives](http://www.basf.com/formulation-additives)