

Irgastab[®] Plus 5170

Product Description	Irgastab Plus 5170 is a synergetic blend of thermal stabilizers for hot melt adhesives to be used during processing or application.
Key Features & Benefits	<ul style="list-style-type: none">- For rubber-based pressure sensitive hot melt adhesives PS-HMA based on SIS /SBS- Tailored to adhesive applications- High resistance to extraction- Long term adhesion protection / retention of adhesive values
Chemical Composition	Proprietary stabilizer blend

Properties

Typical Characteristics	Appearance	white to off-white granules
	Bulk density	~ 520 g/l
	Melting range	160 - 170 °C
	Solubility at 20°C (g/100 g solution)	
	Hexane	~ 1
	Toluene	~ 1

These typical values should not be interpreted as specifications.

Applications

Field of application	Pressure sensitive hot melt adhesives (PS-HMA) based on styrene-block co-polymers (SBC's), such as: styrene-isoprene-styrene (SIS) and styrene-butadiene-styrene (SBS), styrene-ethylene copolymers like SEBS, SEPS, etc., especially when post-processing thermal is required.
Recommended concentrations	The amount required for optimum performance should be determined in laboratory trials and depends on the composition of the adhesive. Irgastab Plus 5170 concentrations of 0.5 – 1% by weight are recommended.

Safety

General	The usual safety precautions when handling chemicals must be observed. These include the measures described in Federal, State, and Local health and safety regulations, thorough ventilation of the workplace, good skin care practices, and wearing of protective goggles.
Safety Data Sheet	All safety information is provided in the Safety Data Sheet for Irgastab Plus 5170.

Storage

Please refer to the "Handling and Storage of Polymer Dispersions" brochure.

Important

While the descriptions, designs, data and information contained herein are presented in good faith and believed to be accurate, they are provided for guidance only. Because many factors may affect processing or application/use, BASF recommends that the reader make tests to determine the suitability of a product for a particular purpose prior to use. **NO WARRANTIES OF ANY KIND, EITHER EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH, OR THAT THE PRODUCTS, DESCRIPTIONS, DESIGNS, DATA OR INFORMATION MAY BE USED WITHOUT INFRINGING THE INTELLECTUAL PROPERTY RIGHTS OF OTHERS.** In no case shall the descriptions, information, data or designs provided be considered a part of BASF's terms and conditions of sale. Further, the descriptions, designs, data, and information furnished by BASF hereunder are given gratis and BASF assumes no obligation or liability for the descriptions, designs, data or information given or results obtained, all such being given and accepted at the reader's risk.

Irgastab is a registered trademark of BASF Group.

© BASF Corporation, 2019



BASF Corporation is fully committed to the Responsible Care® initiative in the USA, Canada, and Mexico.

For more information on Responsible Care, go to:

U.S.: www.basf.us/responsiblecare_usa

Canada: www.basf.us/responsiblecare_canada

México: www.basf.us/responsiblecare_mexico

BASF Corporation

Dispersions and Resins
11501 Steele Creek Road
Charlotte, North Carolina 28273
Phone: (800) 251 – 0612
Email: CustCare-Charlotte@basf.com
Email: edtech-info@basf.com
www.basf.us/dpsolutions