

# Joncryl<sup>®</sup> 1540

<b>Product Description</b>	Joncryl 1540 is a thermosetting acrylic emulsion for industrial coating applications.
<b>Key Features &amp; Benefits</b>	<ul style="list-style-type: none"><li>- Hydroxy functional emulsion</li><li>- Faster cure</li><li>- Good flexibility</li><li>- Good chemical resistance</li><li>- Thermoset</li></ul>
<b>Chemical Composition</b>	Acrylic emulsion

## Properties

<b>Typical Properties</b>	Appearance		semi-translucent emulsion
	Non-volatile at 145°C (2g, 30 minutes)	%	~ 42.5
	pH at 25°C		~ 8.5
	Viscosity at 25°C (Brookfield #2LV, 30 rpm, 30 seconds)	cps	~ 500
	Density at 20°C	g/cm <sup>3</sup> (lbs/gal)	1.03 (8.62)
	Acid number (on solids)		12.65
	OH Equivalent weight (on solids)		985
	Hydroxy number (on solids)		56.9
	MFFT	°C	40
	Tg	°C	42
	Neutralizing Amine		Ammonia
	Freeze-thaw stable		Yes

These typical values should not be interpreted as specifications.

## Application

Joncryl 1540 is a hydroxy functional latex that can be used along with various melamines for waterborne thermoset coatings. Fast cure, chemical resistance, flexibility, and oven stability can be obtained using the recommended starting point formulation (601-BX).

Joncryl 1540 is recommended for applications such as:

- Interior/exterior general metal industrial coating applications
- Interior/exterior machine or equipment coating applications

## Formulation Guidelines

DMEA (dimethyl ethanolamine) is used in this formulation to prevent gelling at 120°F. DMEA will also slow the cure of the melamine, so it is important to balance hot-box stability with performance. If long term hot-box stability is not needed, less DMEA can be used. Raybo<sup>1</sup> 60, which is used for flash rust inhibition, also contains amines which appear to help hot-box stability. Even if you are applying a Joncryl 1540-based coating to non-metallic surfaces, the use of Raybo<sup>1</sup> 60 as a package stabilizer is recommended.

<sup>1</sup>Registered trademark of Raybo Chemical Company.

The use of Nacorr<sup>2</sup> 1552, a corrosion inhibitor, is not typical in waterborne systems. We have found that it is compatible with Joncryl 1540 and has catalytic properties (Nacorr<sup>2</sup> 1552 is a zinc salt of dinonylnaphthalene sulfonic acid). Further studies with Nacorr<sup>2</sup> 1552 and Joncryl 1540 have shown less drift in minimum temperature requirements over time compared to other blocked catalysts. We believe the nature of this combination results in positive synergy between the two. Higher levels of Nacorr<sup>2</sup> 1552 than used in the starting point formulation may result in poor adhesion of a second coat of starting formulation to a previously cured first coat of material (poor inter-coat adhesion).

Only a small amount of associative thickener is required for this formulation. The nature of Joncryl 1540 should allow for high associative thickener efficiency.

The fast cure nature of Formula 601-BX allows the use of Luwipal<sup>®</sup> 066 LF. The use of faster cure, high imino melamines such as Cymel<sup>3</sup> 327 may result in poorer hot-box stability of the coating.

### Starting Point Formulation

The following starting point formulation is recommended for an initial evaluation of Joncryl 1540. Additional optimization of the formulation may be desired to achieve maximum suitability for specific applications.

#### Joncryl 1540 MELAMINE/ACRYLIC WHITE METAL COATING, Formula 601-BX

Materials	Pounds	Gallons
<b>Grind:</b>		
Water	60.7	7.28
Dee Fo <sup>4</sup> 215	2.0	0.27
Surfynol <sup>5</sup> CT-324	11.0	1.25
Ti-Pure <sup>6</sup> R-706	212.7	6.39
<b>Disperse at high speed to 6.5+ Hegman</b>		
Joncryl <sup>®</sup> 1540	546.1	63.36
<b>Premix:</b>		
Luwipal <sup>®</sup> 066 LF	99.5	9.95
Ethylene glycol monobutyl ether	24.6	3.28
DMEA	1.2	0.16
Water	40.0	4.80
<b>Then add:</b>		
Water	14.0	1.37
Nacorr <sup>2</sup> 1552	2.6	0.31
Raybo <sup>1</sup> 60	10.8	1.16
Polyurethane thickener	10.8	0.11
<b>Total</b>	<b>1,026.2</b>	<b>100.01</b>

#### Formulation Attributes

Solids	54.6% by wt, 43.9% by volume
Density	10.3 lbs/gal
PVC	14.5%
VOC (calculated)	35 g/l, 0.3 lbs/gal

<sup>2</sup>Registered trademark of King Industries, Inc.

<sup>3</sup>Registered trademark of Allnex Group.

<sup>4</sup>Registered trademark of Munzing Chemie GmbH.

<sup>5</sup>Registered trademark of Air Products and Chemicals, Inc.

<sup>6</sup>Trademark of The Chemours Company TT, LLC.

## Safety

### General

The usual safety precautions when handling chemicals must be observed. These include the measures described in Federal, State and Local health and safety regulations, thorough ventilation of the workplace, good skin care and wearing of protective goggles.

### Safety Data Sheet

All safety information is provided in the Safety Data Sheet for Joncryl 1540.

## Storage

Please refer to the "Handling and Storage of polymer dispersions" brochure.

## Important

The descriptions, designs, and data contained herein are presented for your guidance only. Because there are many factors under your control which may affect processing or application/use it is necessary for you to make appropriate tests to determine whether the product is suitable for your particular purpose prior to use. **NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, OR INFORMATION SET FORTH, OR THAT THE PRODUCTS, DESIGNS, OR DATA MAY BE USED WITHOUT INFRINGING THE INTELLECTUAL PROPERTY RIGHTS OF OTHERS. IN NO CASE SHALL THE DESCRIPTIONS, DATA OR DESIGNS PROVIDED BE PRESUMED TO BE A PART OF OUR TERMS AND CONDITIONS OF SALE.** Further, you expressly understand and agree that the descriptions, designs, and data furnished by BASF hereunder are given gratis and BASF assumes no obligation or liability for same or results obtained from use thereof, all such being given to you and accepted by you at your risk.

*Joncryl is a registered trademark of BASF Group.*

© BASF Corporation, 2019



BASF Corporation is fully committed to the Responsible Care® Initiative in the USA, Canada, and Mexico.  
For more information on Responsible Care® go to:  
U.S.: [www.basf.us/responsiblecare\\_usa](http://www.basf.us/responsiblecare_usa)  
Canada: [www.basf.us/responsiblecare\\_canada](http://www.basf.us/responsiblecare_canada)  
México: [www.basf.us/responsiblecare\\_mexico](http://www.basf.us/responsiblecare_mexico)

**BASF Corporation**  
Dispersions and Resins  
11501 Steele Creek Road  
Charlotte, North Carolina 28273  
Phone: (800) 251 – 0612  
Email: [CustCare-Charlotte@basf.com](mailto:CustCare-Charlotte@basf.com)  
Email: [edtech\\_info@basf.com](mailto:edtech_info@basf.com)  
[www.basf.us/dpsolutions](http://www.basf.us/dpsolutions)