

Joncryl[®] 1915

Product Description	Joncryl 1915 is a low-cost, block-resistant acrylic emulsion for hardboard primer coatings.
Key Features & Benefits	<ul style="list-style-type: none"> - Excellent Block resistance - Excellent adhesion - Low VOC - Pigment dispersing capability
Chemical Composition	Acrylic emulsion

Properties

Typical Properties	Appearance		semi-translucent emulsion
	Non-volatile at 145°C (2g, 30 minutes)	%	44
	pH at 25°C		8.5
	Viscosity at 25°C (Brookfield #2LV, 30 rpm, 30 seconds)	cps	800
Typical Characteristics	Density at 20°C	g/cm ³ (lbs/gal)	1.02 (8.63)
	MFFT	°C	0
	Tg	°C	43
	Freeze-thaw stable		No

* These typical values should not be interpreted as specifications.

Applications

Joncryl 1915 is a unique acrylic emulsion that has a low minimum film forming temperature yet offers excellent block resistance. Joncryl 1915 is ideally suited for high PVC primers used over hardboard and composite wood substrates.

Joncryl 1915 is recommended for applications such as:

- Interior/exterior primers on wood, hardboard, cement fiberboard, and composite wood applications

Formulation Guidelines

Solvent Levels - Normal primer cure temperatures range from 180 – 250°F maximum board surface temperature. This is generally enough heat to obtain a good performing film, even at PVCs in excess of 55. The addition of low levels of ethylene glycol mono butyl ether, propylene glycol t-butyl ether or propylene glycol n-butyl ether, may further enhance film formation. Caution should be taken not to include too much solvent, as this may encourage blistering or blocking of the coating.

Performance Evaluation

Approximately two wet mils of coating was applied to medium density fiberboard. The panel was baked for 15 minutes at 300°F in an oven. The panel was then immediately placed in an IR oven until a board surface temperature (BST) of 250°F was reached. The panel was allowed to cool to a BST of 150°F before a face-to-face block test was performed. The panel was allowed to cool for a total of 15 minutes before a tape adhesion test was performed.

Block test at 250 psi	No blocking
Adhesion test	Little adhesion failure at coating/substrate interface; mostly substrate failure

Starting Point Formulation

The following starting point formulation is recommended for an initial evaluation of Joncryl 1915. Modification of the formulation may be required to achieve desired results for specific applications.

Joncryl® 1915 HARDBOARD PRIMER, Formula 609-A

Materials	Pounds	Gallons
Joncryl® 1915	245.6	28.45
FoamStar® SI 2292 NC	4.2	0.56
Ti-Pure ¹ R-902	239.1	7.18
DMEA (Dimethyl ethanolamine)	2.5	0.34
Water	37.1	4.45
Atomite ² Calcium carbonate	439.1	19.52
Disperse to 5 Hegman		
Let-down:		
Water	34.0	4.09
Joncryl® 1915	163.7	18.97
Water	132.8	15.94
FoamStar® SI 2292 NC	2.1	0.28
Rheovis® PU 1250 EC	<u>2.0</u>	<u>0.22</u>
Total	1,302.2	100.00

Formulation Attributes

Solids	66% by wt, 49% by volume
Viscosity (Zahn #2)	57 seconds (100 cps)
VOC (calculated)	22 g/l, 0.2 lbs/gal

¹Trademark of The Chemours Company.

²Registered trademark of ECC America Inc. Corporation.

Safety

General

The usual safety precautions when handling chemicals must be observed. These include the measures described in Federal, State and Local health and safety regulations, thorough ventilation of the workplace, good skin care and wearing of protective goggles.

Safety Data Sheet

All safety information is provided in the Safety Data Sheet for Joncryl 1915.

Storage

Please refer to the "Handling and Storage of polymer dispersions" brochure.

Important

WHILE THE DESCRIPTIONS, DESIGNS, DATA AND INFORMATION CONTAINED HEREIN ARE PRESENTED IN GOOD FAITH AND BELIEVED TO BE ACCURATE, THEY ARE PROVIDED FOR GUIDANCE ONLY. BECAUSE MANY FACTORS MAY AFFECT PROCESSING OR APPLICATION/USE, BASF RECOMMENDS THAT THE READER MAKE TESTS TO DETERMINE THE SUITABILITY OF A PRODUCT FOR A PARTICULAR PURPOSE PRIOR TO USE. NO WARRANTIES OF ANY KIND, EITHER EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH, OR THAT THE PRODUCTS, DESCRIPTIONS, DESIGNS, DATA OR INFORMATION MAY BE USED WITHOUT INFRINGING THE INTELLECTUAL PROPERTY RIGHTS OF OTHERS. IN NO CASE SHALL THE DESCRIPTIONS, INFORMATION, DATA OR DESIGNS PROVIDED BE CONSIDERED A PART OF BASF'S TERMS AND CONDITIONS OF SALE. FURTHER, THE DESCRIPTIONS, DESIGNS, DATA, AND INFORMATION FURNISHED BY BASF HEREUNDER ARE GIVEN GRATIS AND BASF ASSUMES NO OBLIGATION OR LIABILITY FOR THE DESCRIPTIONS, DESIGNS, DATA OR INFORMATION GIVEN OR RESULTS OBTAINED, ALL SUCH BEING GIVEN AND ACCEPTED AT THE READER'S RISK.

Joncryl is a registered trademark of BASF Group.

© BASF Corporation, 2025



Responsible Care®
Good Chemistry at Work

BASF Corporation is fully committed to the Responsible Care® Initiative in the USA, Canada, and Mexico.

For more information on Responsible Care® go to:

U.S.: www.basf.us/responsiblecare_usa

Canada: www.basf.us/responsiblecare_canada

México: www.basf.us/responsiblecare_mexico

BASF Corporation

Dispersions and Resins

11501 Steele Creek Road

Charlotte, North Carolina 28273

Phone: (800) 251 – 0612

Email: CustCare-Charlotte@basf.com

www.basf.us/dpsolutions