

Industrial Coatings

Technical Data Sheet

Joncryl® 507 Polyol



Product Description	Joncryl® 507 is a hydroxyl functional acrylic polyol for isocyanate- and melamine-crosslinked coatings.
Key Features & Benefits	<ul style="list-style-type: none">- <i>Narrow molecular weight distribution</i>- <i>n-Butyl acetate version of Joncryl® 500</i>- <i>For use in low odor applications</i>
Chemical Composition	Hydroxyl functional acrylic polyol

Properties

Typical Properties

Appearance	clear liquid
Hydroxyl number of solids	~ 140
Non-volatile at 150°C (0.5g, 60 minutes)	~ 80%
Viscosity at 25.0 ± 0.5°C (Brookfield #4LV, 60 rpm, 30 seconds)	2,500 – 5,500 cP
Density at 20°C	~ 1.05 g/cm ³ (8.73 lbs/gal)
Equivalent weight as supplied, of solids	~ 500, 400
Tg	~ -7°C
Solvent	n-Butyl acetate

These typical values should not be interpreted as specifications.

Applications

Joncryl® 507 is an innovative hydroxyl functional acrylic polymer for high solids systems. Coatings formulated with Joncryl® 507 feature a low viscosity with high solids and excellent flow and leveling with acrylic durability. Joncryl® 507 is recommended for urethane coating applications in the industrial coatings market. Joncryl® 507 is an alternate solvent version of Joncryl® 500 for low odor and non-HAPS applications. More information is available on the Joncryl® 500 technical data sheet.

Joncryl® 507 is recommended for applications such as:

- Interior/exterior automotive refinish applications
- Interior/exterior general metal industrial coating applications

Starting Point Formulation

The following starting point formulation is recommended for an initial evaluation of Joncryl® 507. Additional optimization of the formulation will be required to achieve desired results for specific applications.

Joncryl® 507 GLOSS CLEAR TOPCOAT, Formula 32002-4A

Part A	Pounds	Gallons
Joncryl® 507	468.50	53.67
Efka® FL 3670	0.80	0.10
MAK	171.10	25.16
DBTDL (1% in MAK)	5.00	0.73
Subtotal	645.40	79.66
Part B		
Basonat® HI 100	194.60	19.94
Total	840.00	99.60

Formulation Attributes for Formula 32002-4A

Solids	67.7% by wt, 60.1% by volume
NCO:OH ratio	1.05:1.0
Catalyst level, DBTDL on TRS	0.009%
VOC (calculated)	325 g/l, 2.8 lbs/gal

Safety

General

The usual safety precautions when handling chemicals must be observed. These include the measures described in Federal, State, and Local health and safety regulations, thorough ventilation of the workplace, good skin care, and wearing of personal protective equipment.

Safety Data Sheet

All safety information is provided in the Safety Data Sheet for Joncryl® 507.

Important

While the descriptions, designs, data and information contained herein are presented in good faith and believed to be accurate, they are provided for guidance only. Because many factors may affect processing or application/use, BASF recommends that the reader make tests to determine the suitability of a product for a particular purpose prior to use. **NO WARRANTIES OF ANY KIND, EITHER EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH, OR THAT THE PRODUCTS, DESCRIPTIONS, DESIGNS, DATA OR INFORMATION MAY BE USED WITHOUT INFRINGING THE INTELLECTUAL PROPERTY RIGHTS OF OTHERS.** In no case shall the descriptions, information, data or designs provided be considered a part of BASF's terms and conditions of sale. Further, the descriptions, designs, data, and information furnished by BASF hereunder are given gratis and BASF assumes no obligation or liability for the descriptions, designs, data or information given or results obtained all such being given and accepted at the reader's risk.

Basonat, Efka, and Joncryl are registered trademarks of BASF Group.

© BASF Corporation, 2017



Responsible Care®
Good Chemistry at Work

BASF Corporation is fully committed to the Responsible Care® initiative in the USA, Canada, and Mexico.

For more information on Responsible Care® go to:

U.S.: www.basf.us/responsiblecare_usa

Canada: www.basf.us/responsiblecare_canada

México: www.basf.us/responsiblecare_mexico

U.S & Canada

BASF Corporation

24710 W Eleven Mile Road

Southfield, MI 48034

ph: 1(800) 231-7868

fax: 1(800) 392-7429

Email: DispersionsPigmentsCC@basf.com

Email: edtech-info@basf.com

www.basf.us/dpsolutions

Mexico

BASF Mexicana, S.A. de C.V.

Av. Insurgentes Sur # 975

Col. Ciudad de los Deportes

C.P. 03710

Mexico, D.F.

Phone: (52-55) 5325-2756

Fax: (52-55) 5723-3011