

# Joncryl<sup>®</sup> HPD 496-A

<b>Product Description</b>	Joncryl HPD 496-A is premium performance resin solution that enables highly concentrated pigment dispersions for use in waterbased inks.
<b>Key Features &amp; Benefits</b>	<ul style="list-style-type: none"><li>- supports highly concentrated pigment dispersions</li><li>- superior color development</li><li>- excellent performance with critical pigments</li><li>- excellent rheology and transfer</li><li>- excellent gloss and transparency</li><li>- excellent shock stability with letdown</li><li>- Swiss Ordinance List A compliant</li></ul>
<b>Chemical Composition</b>	Acrylic copolymer

## Properties

<b>Typical Properties</b>	Appearance	clear solution
	Non-volatile	34.5%
	Molecular weight (Mw)	5,500
	Brookfield viscosity at 25°C	500 cP
	pH	8.5
	Acid value	178 mg KOH/g
	Density at 25°C	1.07 g/cm <sup>3</sup>
	Tg	58°C
	Freeze-thaw stable	yes

These typical values should not be interpreted as specifications.

## Application

Joncryl HPD 496-A is a premium performance dispersion resin solution that enables highly pigmented dispersions at low viscosity and with excellent shock stability. This stability allows the dispersions to be used in automated dispensing equipment without the need for further buffering. Joncryl HPD 496-A resin solution improves milling efficiency by allowing faster pigment wetting and particle size reduction, and a higher pigment loading.

## Starting Point Formulation

25.5 parts	Joncryl HPD 496-A
45.0 parts	Organic pigment
0.5 parts	FoamStar <sup>®</sup> SI 2280 defoamer
29.0 parts	Water

## Safety

### General

The usual safety precautions when handling chemicals must be observed. These include the measures described in Federal, State and Local health and safety regulations, thorough ventilation of the workplace, good skin care and wearing of protective goggles.

### Safety Data Sheet

All safety information is provided in the Safety Data Sheet for Joncryl HPD 496-A.

---

## Storage

Please refer to the "Handling and Storage of Polymer Dispersions" brochure.

---

## Important

The descriptions, designs, and data contained herein are presented for your guidance only. Because there are many factors under your control which may affect processing or application/use it is necessary for you to make appropriate tests to determine whether the product is suitable for your particular purpose prior to use. **NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, OR INFORMATION SET FORTH, OR THAT THE PRODUCTS, DESIGNS, OR DATA MAY BE USED WITHOUT INFRINGING THE INTELLECTUAL PROPERTY RIGHTS OF OTHERS. IN NO CASE SHALL THE DESCRIPTIONS, DATA OR DESIGNS PROVIDED BE PRESUMED TO BE A PART OF OUR TERMS AND CONDITIONS OF SALE.** Further, you expressly understand and agree that the descriptions, designs, and data furnished by BASF hereunder are given gratis and BASF assumes no obligation or liability for same or results obtained from use thereof, all such being given to you and accepted by you at your risk.

*Joncryl and FoamStar are registered trademarks of BASF Group.*

© BASF Corporation, 2019



BASF Corporation is fully committed to the Responsible Care® initiative in the USA, Canada, and Mexico.

For more information on Responsible Care® go to:

U.S.: [www.basf.us/responsiblecare\\_usa](http://www.basf.us/responsiblecare_usa)

Canada: [www.basf.us/responsiblecare\\_canada](http://www.basf.us/responsiblecare_canada)

México: [www.basf.us/responsiblecare\\_mexico](http://www.basf.us/responsiblecare_mexico)

### U.S & Canada

BASF Corporation  
24710 W Eleven Mile Road  
Southfield, MI 48034  
ph: 1(800) 231-7868  
fax:1(800) 392-7429  
Email: [CustCare-Charlotte@basf.com](mailto:CustCare-Charlotte@basf.com)  
Email: [edtech-info@basf.com](mailto:edtech-info@basf.com)  
[www.basf.us/dpsolutions](http://www.basf.us/dpsolutions)

### Mexico

BASF Mexicana, S.A. de C.V.  
Av. Insurgentes Sur # 975  
Col. Ciudad de los Deportes  
C.P. 03710  
Mexico, D.F.  
Phone: (52-55) 5325-2756  
Fax: (52-55) 5723-3011