

Industrial Coatings

Technical Data Sheet

Laropal® A 81



Product Description Laropal® A 81 is an aldehyde resin for pigment dispersions.

Key Features & Benefits

- Promotes the natural grain and color of wood
- Good elasticity, adhesion, and hardness
- Excellent toughness

Chemical Composition Condensed products from urea and aliphatic aldehydes

Properties

Typical Properties	Appearance	pastilles
	Acid value	≤ 3 mg KOH/g
	Iodine color number	≤ 3
	Density at 20°C	~ 1.11 g/cm ³ , 9.33 lbs/gal
	Softening range	80 – 95°C
	Tg	~ 57°C, 135°F
	Hydroxyl value	~ 40 mg KOH/g
	Saponification value	~ 65 mg KOH/g

Solubility Soluble in alcohols, esters, ketones, and aromatic hydrocarbons; aliphatic hydrocarbons – solutions tend to separate at temperatures below 15°C, adding 2 – 5% of an aromatic solvent produces stable solutions.

Compatibility Compatible with nitrocellulose, CAB resins, chlorinated rubber, VC copolymers, acrylic resins, urea-formaldehyde resins, melamine-formaldehyde resins, alkyd resins, epoxy resins, and hydrocarbon resins; limited compatibility with ethyl cellulose.

These typical values should not be interpreted as specifications. Solubility and compatibility should be tested for each individual combination.

Applications

Because of its excellent solubility and compatibility, Laropal® A 81 can be used in many types of coating formulations. Depending on the application, it improves gloss, hardness, body, adhesion, and resistance to yellowing.

Because of its good pigment wetting and very low solution viscosity, Laropal® A 81 can be used for the manufacture of pigment pastes with high pigment content.

Laropal® A 81 is very heat stable and can be used in baking finishes, neither causing odor nor discoloration.

Laropal® A 81 is recommended for applications such as:

- Interior/exterior general industrial metal coating applications
- Automotive OEM applications

Fields of Application

Alkyd resins, air- and oven-drying

- Partial replacement of up to 20% solids on solids
- Improvement of resistance to yellowing through excellent heat stability and lightfastness
- Improvement of hardness, gloss, body, and flow
- Cost reduction
- Use as modifying component in alkyd resin production

Universal pigment pastes

- Suitable as grinding resin because of broad compatibility and universal solubility, low solution viscosity, high pigment binding capacity, and transparency

Powder coatings

- Partial replacement of up to 15% of epoxy/polyester or PUR powder
- Improvement of flow due to low melt viscosity

Hot melts for road marking and spray plastics

- Suitable as basic resin in combination with suitable plasticizers due to low melt viscosity, good light fastness, and heat stability
- Improves adhesion to substrates

Performance Properties

	Laropal® A 81	Laropal® A 101
Brightness	1	2
Fastness to light	1	1
Heat resistance	1	1
Compatibility	1	1
Soluble in alcohols	1	1
Soluble in aliphatic hydrocarbons	3	5
Suitable for coatings resistant to water	3	3
Suitable for coatings resistant to mineral oils	2	1
Suitable for coatings resistant to saponification	3	3
Solvent release	3	2
Pigment binding capacity	1	2

1 = very good; 5 = insufficient

Safety

General

The usual safety precautions when handling chemicals must be observed. These include the measures described in Federal, State, and Local health and safety regulations, thorough ventilation of the workplace, good skin care, and wearing of personal protective equipment.

Safety Data Sheet

All safety information is provided in the Safety Data Sheet for Laropal® A 81.

Important

While the descriptions, designs, data and information contained herein are presented in good faith and believed to be accurate, they are provided for guidance only. Because many factors may affect processing or application/use, BASF recommends that the reader make tests to determine the suitability of a product for a particular purpose prior to use. **NO WARRANTIES OF ANY KIND, EITHER EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH, OR THAT THE PRODUCTS, DESCRIPTIONS, DESIGNS, DATA OR INFORMATION MAY BE USED WITHOUT INFRINGING THE INTELLECTUAL PROPERTY RIGHTS OF OTHERS.** In no case shall the descriptions, information, data or designs provided be considered a part of BASF's terms and conditions of sale. Further, the descriptions, designs, data, and information furnished by BASF hereunder are given gratis and BASF assumes no obligation or liability for the descriptions, designs, data or information given or results obtained all such being given and accepted at the reader's risk.

Laropal is a registered trademark of BASF Group.

© BASF Corporation, 2017



BASF Corporation is fully committed to the Responsible Care® initiative in the USA, Canada, and Mexico.

For more information on Responsible Care® go to:

U.S.: www.basf.us/responsiblecare_usa

Canada: www.basf.us/responsiblecare_canada

México: www.basf.us/responsiblecare_mexico

U.S & Canada

BASF Corporation

24710 W Eleven Mile Road

Southfield, MI 48034

ph: 1(800) 231-7868

fax: 1(800) 392-7429

Email: DispersionsPigmentsCC@basf.com

Email: edtech-info@basf.com

www.basf.us/dpsolutions

Mexico

BASF Mexicana, S.A. de C.V.

Av. Insurgentes Sur # 975

Col. Ciudad de los Deportes

C.P. 03710

Mexico, D.F.

Phone: (52-55) 5325-2756

Fax: (52-55) 5723-3011