

Loxanol[®] MI 6730

general

adhesion promoter

- aqueous solution of a cationic polymer

chemical nature

branched polyethyleneimine

Properties

physical form

clear colorless to yellowish liquid

storage

Loxanol[®] MI 6730 should be stored in a cool dry place. High temperatures and direct sunlight can lead to discoloration and the formation of surface films. In case of solidification because of low temperature storage it can briefly be heated up to 80°C preferably under stirring. This has no influence on the performance of the product. Prolonged exposure to atmospheric oxygen can cause discoloration. We therefore recommend storage under an inert atmosphere of nitrogen.

typical properties (no supply specification)

average molar mass (GPC)	~ 750.000 g/mol
viscosity (ISO 2555, Brookfield)	~ 25.000 mPa·s
concentration (ISO 3251)	~ 50 %
water content (DIN 53715)	~ 50 %
refractive index (DIN 51423, 20°C)	~ 1.452
pH value (DIN 19268, 1% dry in distilled water)	~ 11
density (DIN 51757, 20°C)	~ 1.09 g/cm ³
pour point (ISO 3016)	~ -3 °C
residual ethyleneimine	max. 1 ppm

Application

Loxanol® MI 6730 is recommended as primer in coating applications, where it does improve adhesion to the substrate. Especially in UV-curable systems, which often exhibit poor adhesion because of volume shrinkage, considerable improvements can be obtained by using Loxanol® MI 6730.

It is especially effective as an adhesion promoter in multilayer packaging films manufactured by coating, lamination, extrusion coating or co-extrusion. Using Loxanol® MI 6730 in composite films (laminates) allows the use of material combinations that result in improved physical, chemical and mechanical properties and substantially increase the barrier effect.

The following materials are suitable substrates: cellulose, paper, cellophane, viscose, polyolefins (PP, OPP, BOPP, PE, LDPE, HDPE), polyester (PET), polyamide, halogenated polymers (PVC, PVDC) and metals (eg. aluminum).

recommended concentrations

0.5–1 % depending on the application

The solids content of an aqueous Loxanol® MI 6730 primer solution usually is between 0.5 and 1%. Demineralized water should be used. Up to 30 wt% alcohol (methanol, ethanol or isopropanol) can be added to improve drying and wettability. Where films with low surface tensions are used, we recommend the addition of 0.5% nonionic wetting agent. The primer solution should be applied at a coat weight of 1-5g/m².

Contacts worldwide

Asia

BASF East Asia Regional Headquarters Ltd
45/F, Jardine House
No. 1 Connaught Place
Central Hong Kong
China
formulation-additives-asia@basf.com

Europe

BASF SE
Formulation Additives
67056 Ludwigshafen
Germany
formulation-additives-europe@basf.com

North America

BASF Corporation
11501 Steele Creek Road
Charlotte, NC 28273
USA
formulation-additives-nafta@basf.com

South America

BASF S.A
Rochavérá - Crystal Tower
Av. das Nações Unidas, 14.171
Morumbi - São Paulo-SP
Brazil
formulation-additives-south-america@basf.com

Validity

This Technical Data Sheet is valid for all versions of the Loxanol MI 6730.

Safety

When handling these products, please comply with the advice and information given in the safety data sheet and observe protective and workplace hygiene measures adequate for handling chemicals.

Note

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights, etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. The agreed contractual quality of the product results exclusively from the statements made in the product specification. It is the responsibility of the recipient of our product to ensure that any proprietary rights and existing laws and legislation are observed.

® = registered trademark, ™ = trademark of BASF Group, unless otherwise noted

www.basf.com/formulation-additives