

Rheovis[®] PE 1320

general

- Newtonian rheology modifier for aqueous coatings
- specifically designed to improve high brush drag (ICI viscosity) in modern coatings
- excellent application hiding
- excellent flow and leveling properties
- excellent resistance properties
- excellent roller application and spatter resistance

chemical nature

polyether solution in water / butyl diglycol

Properties

physical form

yellow, clear liquid

storage

Rheovis[®] PE 1320 should be stored in tightly closed containers in a cool place. The packed product is not damaged by low temperatures or by frost. If stored at low temperatures precipitation or gelatinization of the product is possible. This process is reversible. Please heat product to room temperature and stir well before use.

typical properties

solvent	water / butyl diglycol
solid content	~ 40%
viscosity (25°C)	~ 1,600 mPa·s

Application

Rheovis[®] PE 1320 is recommended as sole thickener for coating systems which contain a high hydrophobic surface area such as low-pigmented, small-particle-size, high- to semi-gloss coatings. The rheological profile can be further modified by combining Rheovis[®] PE 1320 with other Rheovis[®] associative thickeners.

recommended concentrations

A dosage of 1.0 – 3.0% calculated on total formulation is recommended.

Rheovis[®] PE 1320 is usually added as the final ingredient into a formulation. However, in cases of limited agitation at this stage, adding 10 – 20 % of the total Rheovis[®] PE 1320 quantity just after the grinding stage can aid the incorporation of the thickener.

Contacts worldwide

Asia

BASF East Asia Regional Headquarters Ltd
45/F, Jardine House
No. 1 Connaught Place
Central Hong Kong
China
formulation-additives-asia@basf.com

North America

BASF Corporation
11501 Steele Creek Road
Charlotte, NC 28273
USA
formulation-additives-nafta@basf.com

Europe

BASF SE
Formulation Additives
67056 Ludwigshafen
Germany
formulation-additives-europe@basf.com

South America

BASF S.A
Rochaverá - Crystal Tower
Av. das Nações Unidas, 14.171
Morumbi - São Paulo-SP
Brazil
formulation-additives-south-america@basf.com

Validity

This Technical Data Sheet is valid for all versions of the Rheovis PE 1320:
Rheovis PE 1320, Rheovis PE 1320 NC.

Safety

When handling these products, please comply with the advice and information given in the safety data sheet and observe protective and workplace hygiene measures adequate for handling chemicals.

Note

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights, etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. The agreed contractual quality of the product results exclusively from the statements made in the product specification. It is the responsibility of the recipient of our product to ensure that any proprietary rights and existing laws and legislation are observed.

® = registered trademark, ™ = trademark of BASF Group, unless otherwise noted

www.basf.com/formulation-additives