# Rheovis<sup>®</sup> PU 1214

# **BASF** We create chemistry

general	<ul> <li>polyurethane-based associative thickener</li> <li>non-ionic rheology additive for aqueous systems, low shear thinning</li> <li>designed to improve the application and hiding properties of emulsion paints and adhesives</li> <li>superior hiding power in brush application and minimal roller spatter</li> <li>excellent flow-promoting properties</li> <li>very good scrub and scuff resistances</li> <li>low shear thinning</li> </ul>	
chemical nature	polyurethane polymer in water / butoxytriglycol	
Properties		
physical form	opaque whitish liquid	
storage	Rheovis <sup>®</sup> PU 1214 should be stored in tightly closed containers. The packed product is not damaged by low temperatures or by frost. If stored below 10°C precipitation or gelatinization of the product is possible. This process is reversible. Please heat product to room temperature and stir well before use.	
typical properties	solvent density (25°C) solid content viscosity (25°C) pH value (2% in water)	water / butoxytriglycol ~ 1.068 g/cm <sup>3</sup> ~ 40% ~ 3,500 mPa·s ~ 7
Application	Rheovis <sup>®</sup> PU 1214 is recommended for all paints where excellent rheological properties are important. The main applications are interior and exterior paints which require excellent brush and roller application properties. The rheological behavior of formulations thickened with Rheovis <sup>®</sup> PU 1214 is pH independent. Under shear stress, the reduction of viscosity is distinctly lower than with cellulosic or acrylic thickeners. Rheovis <sup>®</sup> PU 1214 can be combined with other thickeners such as low-	

molecular-weight cellulose derivatives or acrylic thickeners to improve application and storage properties. Because of its low viscosity, Rheovis<sup>®</sup> PU 1214 can be used as supplied. However, it can be diluted with water-soluble co-solvents

**recommended concentrations** A dosage of 0.3 – 1.0% calculated on total formulation is recommended.

(e.g. butyl diglycol) or with water.

## Contacts worldwide

### Asia

BASF East Asia Regional Headquarters Ltd 45/F, Jardine House No. 1 Connaught Place Central Hong Kong China formulation-additives-asia@basf.com

Europe BASF SE Formulation Additives 67056 Ludwigshafen Germany formulation-additives-europe@basf.com North America BASF Corporation 11501 Steele Creek Road Charlotte, NC 28273 USA formulation-additives-nafta@basf.com

South America BASF S.A Rochaverá - Crystal Tower Av. das Naçoes Unidas, 14.171 Morumbi - São Paulo-SP Brazil formulation-additives-south-america@basf.com

### Validity

This Technical Data Sheet is valid for all versions of the Rheovis PU 1214: Rheovis PU 1214, Rheovis PU 1214 NC.

#### Safety

When handling these products, please comply with the advice and information given in the safety data sheet and observe protective and workplace hygiene measures adequate for handling chemicals.

#### Note

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights, etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. The agreed contractual quality of the product results exclusively from the statements made in the product specification. It is the responsibility of the recipient of our product to ensure that any proprietary rights and existing laws and legislation are observed.

 $^{(\!8\!)}$  = registered trademark,  $^{TM}$  = trademark of BASF Group, unless otherwise noted